

SNX-L 62/34 HT

SOLAR CONTROL LAMINATED GLASS.

Triple-silver low-E technology combined with the strength of laminated glass



Laminated Glass


1700 K Street, Washington, DC

BUILD WITH LIGHT®


SNX-L 62/34 HT

- Attractive neutral reflected color.
- Low solar heat gain coefficient: 0.34.
- Capable of withstanding small & large missile tests for hurricane codes.
- Developed to meet building safety codes in North America.

SNX-L 62/34 HT is ideal for applications requiring safety, security, hurricane or ballistic resistance and can help projects qualify for LEED credits. Available through the independent network of Guardian Select® Fabricators. To locate a Select Fabricator, visit www.SunGuardGlass.com.



Insulating Glass Data



Product	Outboard - Inboard Substrate	PVB Thickness	Transmittance			Reflectance			U-Value Winter Nighttime		Relative Heat Gain	Solar Heat Gain Co-efficient	Light to Solar Gain (LSG)
			Visible Light %	Ultra-violet %	Solar Energy %	Visible Light Out %	Visible Light In %	Solar Energy Out %					
									Air	Argon			
Monolithic Laminated												6 mm/PVB/6 mm	
SNX-L 62/34	UltraClear - UltraClear	.060	64	0	26	15	17	51	0.95	n/a	87	0.32	1.98
		.090	63	0	25	15	17	51	0.94	n/a	86	0.32	1.99
	Clear - Clear	.060	61	0	24	15	16	40	0.95	n/a	91	0.34	1.80
		.090	61	0	24	15	16	40	0.94	n/a	90	0.34	1.80
Insulating Glass - Laminated												6 mm/PVB/6 mm/12.7 mm a.s./6 mm	
SNX-L 62/34	UltraClear - UltraClear	.060	59	0	24	18	23	52	0.46	0.43	70	0.27	2.14
		.090	58	0	23	18	22	52	0.45	0.43	69	0.27	2.15
	Clear - Clear	.060	56	0	22	18	22	41	0.46	0.43	70	0.28	2.01
		.090	55	0	21	18	21	41	0.45	0.43	70	0.27	2.01

- The performance values shown are nominal and subject to variations due to manufacturing tolerances.
- Guardian performance data are calculated for center-of-glass only (no spacer or framing) in accordance with the LBNL Window 7 program.
- Relative Heat Gain, Solar Heat Gain Coefficient and/or LSG may change slightly when using argon gas fill.
- Guardian reserves the right to change product performance characteristics without notice or obligation.

To learn more, call us at
1-866-GuardSG (482-7374) or visit us online
www.SunGuardGlass.com